

3255

Conductor

Description

3255 is a silver conductor paste designed to screen print solderable electrodes onto a variety of electrical ceramic component devices. The fired film forms a highly adherent bond to many types of substrates, including piezoelectric transducers (PZTs), NTC thermistors, alumina, steatite and porcelain. The metalized electrode is solderable for external lead attachments.

Key Features

- Excellent adhesion
- Excellent solderability
- Compatible on piezoelectric transducers (PZTs), NTC thermistors, alumina, steatite and porcelain



This picture does not show the packaging of 3255 and is solely intended for illustration purposes. The products are available in different packaging configurations and may change over time. Please refer to the latest safety data sheets for safety-relevant pictograms

Typical Properties

Viscosity	110-130 kcps Brookfield RVT spindle #7, at 20 rpm, 25 °C
Alloy Ratio	100
Coverage	98 cm ² /gm at 25 um fired film thickness
Metal	Ag
Color	Silver

Recommended Processing Guide

Process Temperature (TDS)	725-850 °C peak temperature. Dwell time 8-12 minutes at peak. Cycle time of 45-60 minutes. Larger parts may require a longer firing profile.
Film Thickness	8-14 um

3255
Conductor

Warranty

6 months

Americas	Asia Pacific	China	Europe, Middle East and Africa
Phone +1 610 825 6050 electronics.americas@heraeus.com	Phone +65 6571 7649 electronics.apac@heraeus.com	Phone +86 53 5815 9601 electronics.china@heraeus.com	Phone +49 6181 35 4370 electronics.emea@heraeus.com

The descriptions and engineering data shown here have been compiled by Heraeus using commonly accepted procedures, in conjunction with modern testing equipment, and have been compiled as according to the latest factual knowledge in our possession. The information was up-to date on the date this document was printed (latest versions can always be supplied upon request). Although the data is considered accurate, we cannot guarantee accuracy, the results obtained from its use, or any patent infringement resulting from its use (unless this is contractually and explicitly agreed in writing, in advance). The data is supplied on the condition that the user shall conduct tests to determine materials suitability for particular application. The Heraeus logo and Heraeus, figurative mark are trademarks or registered trademarks of Heraeus Holding GmbH or its affiliates. All rights reserved.