

AD 1688-06

Conductor

Description

The air dry silvers are used to make non-conductive surfaces electrically and thermally conductive. They can be used in circuit repair or as RF shielding materials. Most can be brushed, sprayed or dipped. These materials will cure at room temperature in 16-20 hours or in 30 minutes at 120-200°C. A heat gun will cure the material in seconds. The conductivity of the film can be increased by repeated application of layers.

Key Features

- Electrically and thermally conductive
- Curable at room temperature
- Available in a range of Ag loadings
- High adhesion to most materials
- Solvent resistant



This picture does not show the packaging of AD 1688-06 and is solely intended for illustration purposes. The products are available in different packaging configurations and may change over time. Please refer to the latest safety data sheets for safety-relevant pictograms.

Typical Properties

Viscosity	2.7-3.3 kcps, Brookfield LVT, #5 spindle at 30 rpm in 2 oz. jar at 25°C
Solids	68% ± 1%
Alloy Ratio	100
Metal	Ag
Color	Silver

Recommended Processing Guide

Process Temperature (TDS)	Room temperature in 16-20 hours or in 30 minutes at 120-200°C.
---------------------------	--

AD 1688-06

Conductor

Warranty

6 months

Americas

Phone +1 610 825 6050

electronics.americas@heraeus.com

Asia Pacific

Phone +65 6571 7649

electronics.apac@heraeus.com

China

Phone +86 53 5815 9601

electronics.china@heraeus.com

Europe, Middle East and Africa

Phone +49 6181 35 4370

electronics.emea@heraeus.com

The descriptions and engineering data shown here have been compiled by Heraeus using commonly accepted procedures, in conjunction with modern testing equipment, and have been compiled as according to the latest factual knowledge in our possession. The information was up-to date on the date this document was printed (latest versions can always be supplied upon request). Although the data is considered accurate, we cannot guarantee accuracy, the results obtained from its use, or any patent infringement resulting from its use (unless this is contractually and explicitly agreed in writing, in advance). The data is supplied on the condition that the user shall conduct tests to determine materials suitability for particular application. The Heraeus logo and Heraeus, figurative mark are trademarks or registered trademarks of Heraeus Holding GmbH or its affiliates. All rights reserved.