Heraeus

AGCL-675

Polymer Thick Film

Description

AGCL-675 Silver/Silver Chloride Ink is an electrically conductive ink designed to be applied in manufacturing by screen printing, dipping and various other print methods. The ink is suited for printed disposable defibrillator pads; EKG and EEG reference electrodes; and other biomedical sensors. Other AGCL ink formulations are available with different silver to silver chloride ratios for varying interaction of electronic signals in medical devices.

Key Features

- Screen print, dip, or thin for gravure print
- Compatible with AG-510 for overprint
- Dries to an optimal surface finish for enhancing electrode interaction
- Extremely tough; crease and scuff resistant
- Compatible with out UV curable dielectrics, conductive epoxy adhesives and UV curable component encapsulants
- Ratio silver to silver chloride: 72.5/27.5
- Other Blended ratios are available



Typical Properties	
Viscosity	5.5-14.6 Kcps. Brookfield SC4-14 spindle @ SR 20, 25°C
Solids	66-70%
Metal	AGCL
Color	Light Silver
	<50 μm

Recommended Processing Guide	
Printing Parameters	Monofilament polyester (157 to 230 mesh) is recommended
Recommended Thinner	Call for recommendation

Heraeus Electronics

AGCL-675

Polymer Thick Film

Heraeus

AGCL-675

Polymer Thick Film

Warranty

6 months

Storage

Store at ambient conditions away from direct light. Material should be thoroughly mixed or rolled on a jar roller at a slow speed for 1 hour prior to use

Americas

Phone +1 610 825 6050

electronics.americas@heraeus.com

Asia Pacific

electronics.apac@heraeus.com

Phone +65 6571 7649

China

Phone +86 53 5815 9601 electronics.china@heraeus.com

Europe, Middle East and Africa

Phone +49 6181 35 4370 electronics.emea@heraeus.com

The descriptions and engineering data shown here have been compiled by Heraeus using commonly accepted procedures, in conjunction with modern testing equipment, and have been compiled as according to the latest factual knowledge in our possession. The information was up-to date on the date this document was printed (latest versions can always be supplied upon request). Although the data is Å considered accurate, we cannot guarantee accuracy, the results obtained from its use, Å or any Å patent Å infringement Å resulting Å from Å its Å use Å (unless Å this Å is contractually and explicitly agreed in writing, in advance). The data is supplied on the condition that the user shall conduct tests to determine materials suitability for particular application. Å The Heraeus logo and Heraeus, figurative mark are trademarks or registered trademarks of Heraeus Holding GmbH or its affiliates. All rights reserved.