AGCL-807 (Ratio 60:40)

Description

AGCL-807 Silver/Silver Chloride Ink is an electrically conductive ink with the AG to AGCL ratio of 60/40 designed to be applied in manufacturing by screen printing, dipping and various other print methods. The ink is suited for printed disposable defibrillator pads, EKG and EEG reference electrodes, and other biomedical sensors. Other AGCL ink formulations are available with different silver to silver chloride ratios for varying interaction of electronic signals in medical devices.

Key Features

- Compatible with AG-510 and Ag-888 as an overprint
- Dries to a smooth surface finish in order to optimize surface area contact for enhanced electrode interaction
- Designed to dry quickly after printing
- Extremely tough; crease and scuff resistant
- Ratio silver to silver chloride: 60:40 other ratios are available



This picture does not show the packaging of AGCL-807 and is solely intended for illustration purposes. The products are available in different packaging configurations and may change over time. Please refer to the latest safety data sheets for safety-relevant pictograms

Typical Properties	
Viscosity	7.5 – 14.7 kcps, Brookfield, SC4-14 spindle @ SR 20, 25°C
Conductivity	<.075 Ω/sq/mil
Solids	68.0 ± 2.0%
Color	Light Silver
Particle Size	<50 µm, hegman

Recommended Processing Guide	
Printing Parameters	Polyester Mesh (180 to 260 TPI) Stainless not compatible.
Drying Temperature	100-130°C
Film Thickness	10-20 µm DFT
Recommended Thinner	Glycol Ether/PM Acetate
Paste Compatibility	Compatible with all PriElex dielectrics.

AGCL-807 (Ratio 60:40)

Warranty

Material guaranteed to meet specifications for 6 months from date of manufacturing with proper storage. Do not allow to come in contact with ANY metal for any period of time. This includes but is not limited to mixing, processing, and storage. This material is also white light reactive.

Storage

Ambient storage, mix well prior to use, Avoid white light exposure. CANNOT CONTACT METAL.

Americas	Asia Pacific	China	Europe, Middle East and Africa
Phone +1 610 825 6050	Phone +65 6571 7649	Phone +86 53 5815 9601	Phone +49 6181 35 4370
electronics.americas@heraeus.com	electronics.apac@heraeus.com	electronics.china@heraeus.com	electronics.emea@heraeus.com

The descriptions and engineering data shown here have been compiled by Heraeus using commonly accepted procedures, in conjunction with modern testing equipment, and have been compiled as according to the latest factual knowledge in our possession. The information was up-to date on the date this document was printed (latest versions can always be supplied upon request). Although the data is considered accurate, we cannot guarantee accuracy, the results obtained from its use, or any patent infringement resulting from its use (unless this is contractually and explicitly agreed in writing, in advance). The data is supplied on the condition that the user shall conduct tests to determine materials suitability for particular application. The Heraeus logo and Heraeus, figurative mark are trademarks or registered trademarks of Heraeus Holding GmbH or its affiliates. All rights reserved.

All changes are based on information displayed using the template data_sheet/HET/TFM/print_data_sheet.html.twig.
Version (last updated) 12 Nov 2026

Heraeus Electronics GmbH & Co.KG, 63450 Hanau, Germany
www.heraeus-electronics.com