

BE703050-BT5

Buried Electrode

Description

The Ag/Pd powders contained in these pastes are alloyed, micro-fine particles. The organic system has been developed to be compatible with a wide range of tape systems. The pastes can also be customized with customer specific inorganic additives to minimize shrinkage mismatch and optimize electrical properties.

Key Features

- BT based dielectrics



This picture does not show the packaging of BE703050-BT5 and is solely intended for illustration purposes. The products are available in different packaging configurations and may change over time. Please refer to the latest safety data sheets for safety-relevant pictograms.

Typical Properties

Viscosity	20-40 Kcps, Brookfield RVT Spindle #14 @ 10 rpm, 25°C
Solids	55% ± 1%
Alloy Ratio	70 : 30
Metal	AgPd

Recommended Processing Guide

Process Temperature (TDS)	1115-1130°C peak temperature
---------------------------	------------------------------

BE703050-BT5

Buried Electrode

Warranty

6 months

Americas

Phone +1 610 825 6050

electronics.americas@heraeus.com

Asia Pacific

Phone +65 6571 7649

electronics.apac@heraeus.com

China

Phone +86 53 5815 9601

electronics.china@heraeus.com

Europe, Middle East and Africa

Phone +49 6181 35 4370

electronics.emea@heraeus.com

The descriptions and engineering data shown here have been compiled by Heraeus using commonly accepted procedures, in conjunction with modern testing equipment, and have been compiled as according to the latest factual knowledge in our possession. The information was up-to date on the date this document was printed (latest versions can always be supplied upon request). Although the data is considered accurate, we cannot guarantee accuracy, the results obtained from its use, or any patent infringement resulting from its use (unless this is contractually and explicitly agreed in writing, in advance). The data is supplied on the condition that the user shall conduct tests to determine materials suitability for particular application. The Heraeus logo and Heraeus, figurative mark are trademarks or registered trademarks of Heraeus Holding GmbH or its affiliates. All rights reserved.

All changes are based on information displayed using the template `data_sheet/HET/TFM/print_data_sheet.html.twig`.
Version (last updated) 26 Feb 2026

Heraeus Electronics GmbH & Co.KG, 63450 Hanau, Germany
Web: www.heraeus-electronics.com