

C2030

Conductor

Description

C2030 is a screen printable 3.0:1 Silver/Palladium paste and general-purpose fritted conductor material, suitable for a wide variety of applications, where excellent performance is called for. It is also ideal for use as a resistor termination.

Key Features

- Excellent solderability and leach resistance
- Solderable on alumina and HERAEUS dielectrics
- Compatible with HERAEUS resistors and dielectrics
- Excellent initial and aged adhesion, even after multiple firings on alumina and when fired on dielectrics



This picture does not show the packaging of C2030 and is solely intended for illustration purposes. The products are available in different packaging configurations and may change over time. Please refer to the latest safety data sheets for safety-relevant pictograms.

Typical Properties

Viscosity	30-50 Pas (25 °C, D = 100/s)
Solids	78.0% ± 1.5 %
Alloy Ratio	03:01
Coverage	80 cm ² /g (FFT: 12 µm)
Metal	AgPd
Color	Dark Grey

Recommended Processing Guide

Printing Parameters	Print through a 200-325 mesh. stainless steel screen.
Printing Speed	Up to at least 20 cm/s
Drying Temperature	Dry at 125-50 °C for 10-15 minutes
Process Temperature (TDS)	Fire at 850 °C (peak) for 10 minutes, and with a total firing cycle time of c. 30-60 minutes.
Film Thickness	12.0-15.5 µm
Recommended Thinner	HVS 100
Paste Compatibility	Dielectrics: IP9117 Series, Resistors: R8900 Series, R8900D Series

C2030

Conductor

Warranty

12 months

Storage

Store in a dry and cool condition at 2-23 °C in a dark place with container tightly shut, When stored in a refrigerator, the paste should have acquired room temperature before being opened,

Americas

Phone +1 610 825 6050

electronics.americas@heraeus.com

Asia Pacific

Phone +65 6571 7649

electronics.apac@heraeus.com

China

Phone +86 53 5815 9601

electronics.china@heraeus.com

Europe, Middle East and Africa

Phone +49 6181 35 4370

electronics.emea@heraeus.com

The descriptions and engineering data shown here have been compiled by Heraeus using commonly accepted procedures, in conjunction with modern testing equipment, and have been compiled as according to the latest factual knowledge in our possession. The information was up-to date on the date this document was printed (latest versions can always be supplied upon request). Although the data is considered accurate, we cannot guarantee accuracy, the results obtained from its use, or any patent infringement resulting from its use (unless this is contractually and explicitly agreed in writing, in advance). The data is supplied on the condition that the user shall conduct tests to determine materials suitability for particular application. The Heraeus logo and Heraeus, figurative mark are trademarks or registered trademarks of Heraeus Holding GmbH or its affiliates. All rights reserved.