

## C2160

### Conductor

#### Description

C2160 is a Pd/Ag composition designed for hybrid applications and application where more leach resistance is required. The C2160 conductor is suitable for a wide variety of applications such as automotive electronics, power hybrids and commercial application where more stringent requirements exist. It exhibits excellent solderability, aged adhesion properties and is aluminum wire bondable.

#### Key Features

- Excellent solderability and leach resistance
- Excellent long term adhesion
- Good Al wire bond adhesion (initial and aged)



*This picture does not show the packaging of C2160 and is solely intended for illustration purposes. The products are available in different packaging configurations and may change over time. Please refer to the latest safety data sheets for safety-relevant pictograms.*

#### Typical Properties

Viscosity	150-220 Kcps Brookfield HBTSC4-14 spindle, 6R utility cup at 10 rpm, 25 °C
Solids	79.0 ± 1.0 %
Alloy Ratio	06:01
Coverage	80 cm <sup>2</sup> /g at 12 um fired film thickness
Metal	AgPd
Color	Dark Grey

#### Recommended Processing Guide

Process Temperature (TDS)	850 °C peak temperature. 10 minutes at peak. Total cycle time 30-60 minutes.
Film Thickness	10-15 um

### C2160

#### Conductor

---

#### Warranty

6 months

#### Americas

Phone +1 610 825 6050

[electronics.americas@heraeus.com](mailto:electronics.americas@heraeus.com)

#### Asia Pacific

Phone +65 6571 7649

[electronics.apac@heraeus.com](mailto:electronics.apac@heraeus.com)

#### China

Phone +86 53 5815 9601

[electronics.china@heraeus.com](mailto:electronics.china@heraeus.com)

#### Europe, Middle East and Africa

Phone +49 6181 35 4370

[electronics.emea@heraeus.com](mailto:electronics.emea@heraeus.com)

The descriptions and engineering data shown here have been compiled by Heraeus using commonly accepted procedures, in conjunction with modern testing equipment, and have been compiled as according to the latest factual knowledge in our possession. The information was up-to date on the date this document was printed (latest versions can always be supplied upon request). Although the data is considered accurate, we cannot guarantee accuracy, the results obtained from its use, or any patent infringement resulting from its use (unless this is contractually and explicitly agreed in writing, in advance). The data is supplied on the condition that the user shall conduct tests to determine materials suitability for particular application. The Heraeus logo and Heraeus, figurative mark are trademarks or registered trademarks of Heraeus Holding GmbH or its affiliates. All rights reserved.