

## C2360

### Conductor

#### Description

C2360 is a silver/palladium (6:1) high solids conductor paste designed for hybrid applications utilizing aluminum nitride. It exhibits good solderability and excellent adhesion.

#### Key Features

- Excellent solderability
- Excellent adhesion to aluminum nitride



*This picture does not show the packaging of C2360 and is solely intended for illustration purposes. The products are available in different packaging configurations and may change over time. Please refer to the latest safety data sheets for safety-relevant pictograms.*

#### Typical Properties

Viscosity	150-220 Pa-s, Brookfield HBT, DVIII SC4-14 spindle, 6R utility cup at 10 rpm, 25 °C
Solids	83.0 ± 1.0 %
Alloy Ratio	06:01
Metal	AgPd
Color	Dark Grey

#### Recommended Processing Guide

Process Temperature (TDS)	850 °C peak temperature. Dwell time for 10 minutes.
Film Thickness	13-16 um

### C2360

#### Conductor

---

#### Warranty

6 months

#### Americas

Phone +1 610 825 6050

electronics.americas@heraeus.com

#### Asia Pacific

Phone +65 6571 7649

electronics.apac@heraeus.com

#### China

Phone +86 53 5815 9601

electronics.china@heraeus.com

#### Europe, Middle East and Africa

Phone +49 6181 35 4370

electronics.emea@heraeus.com

The descriptions and engineering data shown here have been compiled by Heraeus using commonly accepted procedures, in conjunction with modern testing equipment, and have been compiled as according to the latest factual knowledge in our possession. The information was up-to date on the date this document was printed (latest versions can always be supplied upon request). Although the data is considered accurate, we cannot guarantee accuracy, the results obtained from its use, or any patent infringement resulting from its use (unless this is contractually and explicitly agreed in writing, in advance). The data is supplied on the condition that the user shall conduct tests to determine materials suitability for particular application. The Heraeus logo and Heraeus, figurative mark are trademarks or registered trademarks of Heraeus Holding GmbH or its affiliates. All rights reserved.