

### C3605S

#### Conductor

##### Description

C3605P and C3605S are pastes only consisting of Ptpowder and organic vehicle. They are intended to be mixed with customer specific adhesion promoters or to be co-fired with tape. C3605P and C3605S can – depending on the exact viscosity which is delivered – be either sprayed/brushed (“P”- version) or screen printed (“S”- version). They are particularly useful for the manufacture of O2 sensors.

##### Key Features

- Fritless pastes
- Chemically resistant
- Can be used on alumina, zirconia or other bodies



*This picture does not show the packaging of C3605S and is solely intended for illustration purposes. The products are available in different packaging configurations and may change over time. Please refer to the latest safety data sheets for safety-relevant pictograms.*

##### Typical Properties

Viscosity	30-45 Pas (25 °C, D = 50 /s)
Alloy Ratio	100
Metal	Pt
Color	Silver

##### Recommended Processing Guide

Process Temperature (TDS)	Fire at 1100-1500 °C (peak) for 5-30 minutes, and with a total firing cycle time of c. 30-60 minutes.
---------------------------	---

### C3605S

#### Conductor

---

#### Warranty

6 months

#### Americas

Phone +1 610 825 6050

[electronics.americas@heraeus.com](mailto:electronics.americas@heraeus.com)

#### Asia Pacific

Phone +65 6571 7649

[electronics.apac@heraeus.com](mailto:electronics.apac@heraeus.com)

#### China

Phone +86 53 5815 9601

[electronics.china@heraeus.com](mailto:electronics.china@heraeus.com)

#### Europe, Middle East and Africa

Phone +49 6181 35 4370

[electronics.emea@heraeus.com](mailto:electronics.emea@heraeus.com)

The descriptions and engineering data shown here have been compiled by Heraeus using commonly accepted procedures, in conjunction with modern testing equipment, and have been compiled as according to the latest factual knowledge in our possession. The information was up-to date on the date this document was printed (latest versions can always be supplied upon request). Although the data is considered accurate, we cannot guarantee accuracy, the results obtained from its use, or any patent infringement resulting from its use (unless this is contractually and explicitly agreed in writing, in advance). The data is supplied on the condition that the user shall conduct tests to determine materials suitability for particular application. The Heraeus logo and Heraeus, figurative mark are trademarks or registered trademarks of Heraeus Holding GmbH or its affiliates. All rights reserved.