

### C6011

#### Conductor

##### Description

C6011 is a screen printable, non-solderable Gold/Palladium/Platinum conductor paste for fuel sensor application. C6011 is optimized in hardness and surface density. It shows excellent printability resulting in high line definition and smooth surface under various drying conditions.

##### Key Features

- Most suitable material for low sulphur fuel application because of absence of silver Very smooth fired surface which exhibits very durable mechanical resistance and chemically extremely resistant



*This picture does not show the packaging of C6011 and is solely intended for illustration purposes. The products are available in different packaging configurations and may change over time. Please refer to the latest safety data sheets for safety-relevant pictograms.*

##### Typical Properties

Conductivity	≤ 100 milliohms/square (FFT: 10 μm)
Viscosity	25 – 45 Pas (25 °C, D = 100/s)
Solids	84.0 % ± 1.5 %
Coverage	c. 75 cm <sup>2</sup> / g (@ FFT 10 μm)
Metal	AuPtPd

##### Recommended Processing Guide

Printing Parameters	Print through a 200 - 325 mesh stainless steel screen. 0.03 – 0.04 mm Ø wire and 20 – 30 μm emulsion. Level at room temperature for 10 minutes.
Drying Temperature	Dry at max. 150 °C for 8 – 10 minutes
Process Temperature (TDS)	Fire at 850 °C (peak) for 10 minutes, and with a total firing cycle time of c. 30 – 60 minutes
Film Thickness	8 – 14 μm
Recommended Thinner	HVS 100

### C6011

#### Conductor

---

#### Warranty

6 months

#### Storage

store in a dry, cool (5 – 25 °C) and dark place with container tightly shut

#### Americas

Phone +1 610 825 6050

[electronics.americas@heraeus.com](mailto:electronics.americas@heraeus.com)

#### Asia Pacific

Phone +65 6571 7649

[electronics.apac@heraeus.com](mailto:electronics.apac@heraeus.com)

#### China

Phone +86 53 5815 9601

[electronics.china@heraeus.com](mailto:electronics.china@heraeus.com)

#### Europe, Middle East and Africa

Phone +49 6181 35 4370

[electronics.emea@heraeus.com](mailto:electronics.emea@heraeus.com)

The descriptions and engineering data shown here have been compiled by Heraeus using commonly accepted procedures, in conjunction with modern testing equipment, and have been compiled as according to the latest factual knowledge in our possession. The information was up-to date on the date this document was printed (latest versions can always be supplied upon request). Although the data is considered accurate, we cannot guarantee accuracy, the results obtained from its use, or any patent infringement resulting from its use (unless this is contractually and explicitly agreed in writing, in advance). The data is supplied on the condition that the user shall conduct tests to determine materials suitability for particular application. The Heraeus logo and Heraeus, figurative mark are trademarks or registered trademarks of Heraeus Holding GmbH or its affiliates. All rights reserved.

All changes are based on information displayed using the template `data_sheet/HET/TFM/print_data_sheet.html.twig`.  
Version (last updated) 04 May 2026