

DT1749L-1

Component Metallization

Description

DT1749L-1 is a lead free silver paste for backside conductor of chip resistors, which with low silver content. DT1749L-1 exhibits excellent leaching property, acid-resistance property, adhesive property and electrical characteristics.

Typical Properties

Viscosity	120 – 180kcps, Brookfield HBDV–III Ultra, SC4-14 spindle & 6R utility cup @ 10 rpm, 25°C
Solids	59.0 ± 2.0%

Key Features

- Excellent leaching property Excellent acid-resistant property Excellent adhesive property Excellent electrical characteristics



DT1749L-1

Component Metallization

Recommended Processing Guide

Printing Parameters	200- 400 mesh Polyester or stainless steel screen
Drying Temperature	130 °C for 15 minutes, with exhaust system 150 °C for 10 minutes
Process Temperature (TDS)	Peak temp : 840~860 °C Dwell time : 8~15 minutes
Recommended Thinner	Heraeus SRV-372

Americas

Phone +1 610 825 6050

electronics.americas@heraeus.com

Asia Pacific

Phone +65 6571 7649

electronics.apac@heraeus.com

China

Phone +86 53 5815 9601

electronics.china@heraeus.com

Europe, Middle East and Africa

Phone +49 6181 35 4370

electronics.emea@heraeus.com

The descriptions and engineering data shown here have been compiled by Heraeus using commonly accepted procedures, in conjunction with modern testing equipment, and have been compiled as according to the latest factual knowledge in our possession. The information was up-to date on the date this document was printed (latest versions can always be supplied upon request). Although the data is considered accurate, we cannot guarantee accuracy, the results obtained from its use, or any patent infringement resulting from its use (unless this is contractually and explicitly agreed in writing, in advance). The data is supplied on the condition that the user shall conduct tests to determine materials suitability for particular application. The Heraeus logo and Heraeus, figurative mark are trademarks or registered trademarks of Heraeus Holding GmbH or its affiliates. All rights reserved.

DT1749L-1

Component Metallization

Warranty

Material guaranteed to meet specifications for 6 months from date of manufacturing with proper storage.

Storage

Store in a dry, cool (5 - 25°C), dark place with container tightly shut. Allow paste to come to room temperature prior to opening. Spatulate well before using.

Americas

Phone +1 610 825 6050

electronics.americas@heraeus.com

Asia Pacific

Phone +65 6571 7649

electronics.apac@heraeus.com

China

Phone +86 53 5815 9601

electronics.china@heraeus.com

Europe, Middle East and Africa

Phone +49 6181 35 4370

electronics.emea@heraeus.com

The descriptions and engineering data shown here have been compiled by Heraeus using commonly accepted procedures, in conjunction with modern testing equipment, and have been compiled as according to the latest factual knowledge in our possession. The information was up-to date on the date this document was printed (latest versions can always be supplied upon request). Although the data is considered accurate, we cannot guarantee accuracy, the results obtained from its use, or any patent infringement resulting from its use (unless this is contractually and explicitly agreed in writing, in advance). The data is supplied on the condition that the user shall conduct tests to determine materials suitability for particular application. The Heraeus logo and Heraeus, figurative mark are trademarks or registered trademarks of Heraeus Holding GmbH or its affiliates. All rights reserved.