

## IP9025S

### Dielectric / Glaze

#### Description

IP9025S is a screen printable resistor overglaze paste. It fires to a glossy, green transparent color, for optimum laser-trim characteristics. It is fully compatible with the R8900 and R8900D resistor Series, and enhances the stability of such resistors.

#### Key Features

- Hermetic protection
- Compressively expansion-matched, for a high resistor stability
- Allows for a reliable use of high silver internal interconnects
- High-speed printing may be realized

#### Typical Properties

Viscosity	25-45 Pas (25 °C, D = 100/s)
Coverage	c. 100 cm <sup>2</sup> /g (FFT2: 10 um)
Color	Green, transparent

#### Recommended Processing Guide

Process Temperature (TDS)	Fire at 490 – 525 °C (peak) for 2 – 3 minutes (500 – 510 °C is optimal), and with a total firing cycle time of c. 30 minutes
---------------------------	--



*This picture does not show the packaging of IP9025S and is solely intended for illustration purposes. The products are available in different packaging configurations and may change over time. Please refer to the latest safety data sheets for safety-relevant pictograms.*

#### Americas

Phone +1 610 825 6050

electronics.americas@heraeus.com

#### Asia Pacific

Phone +65 6571 7649

electronics.apac@heraeus.com

#### China

Phone +86 53 5815 9601

electronics.china@heraeus.com

#### Europe, Middle East and Africa

Phone +49 6181 35 4370

electronics.emea@heraeus.com

The descriptions and engineering data shown here have been compiled by Heraeus using commonly accepted procedures, in conjunction with modern testing equipment, and have been compiled as according to the latest factual knowledge in our possession. The information was up-to date on the date this document was printed (latest versions can always be supplied upon request). Although the data is considered accurate, we cannot guarantee accuracy, the results obtained from its use, or any patent infringement resulting from its use (unless this is contractually and explicitly agreed in writing, in advance). The data is supplied on the condition that the user shall conduct tests to determine materials suitability for particular application. The Heraeus logo and Heraeus, figurative mark are trademarks or registered trademarks of Heraeus Holding GmbH or its affiliates. All rights reserved.

All changes are based on information displayed using the template data\_sheet/HET/TFM/print\_data\_sheet.html.twig.  
Version (last updated) 26 Feb 2026

Heraeus Electronics GmbH & Co.KG, 63450 Hanau, Germany  
Web: www.heraeus-electronics.com