Heraeus

IP9029H

Dielectric / Glaze

Description

IP9029H is a green dielectric, particularly developed for use as an acid–resistant overglaze on chip and standard resistors.

Key Features

- It can withstand plating solutions, eg Ni baths with pHvalues of 4-5 and Pb/Sn baths with pH-values of < 1
- Also resistant to mildly alkaline solutions



This picture does not show the packaging of IP9029H and is solely intended for illustration purposes. The products are available in different packaging configurations and may change over time. Please refer to the latest safety data sheets for safety-relevant pictograms.

Typical Properties				
Viscosity	25-45 Pas (25 °C, D = 100/s)			
Coverage	c. 111 cm2/g (FFT: 15 um)			
Metal	None			
Color	Green, transparent			
Recommended Processing Guide				
Process Temperature (TDS)	Fire at 580-620 °C (peak) for 2 minutes, and with a total firing cycle time of c. 25- 30 minutes.			
Film Thickness	14-18 um			

Americas	Asia Pacific	China	Europe, Middle East and Africa
Phone +1 610 825 6050	Phone +65 6571 7649	Phone +86 53 5815 9601	Phone +49 6181 35 4370
electronics.americas@heraeus.com	electronics.apac@heraeus.com	electronics.china@heraeus.com	electronics.emea@heraeus.com

The descriptions and engineering data shown here have been compiled by Heraeus using commonly accepted procedures, in conjunction with modern testing equipment, and have been compiled as according to the latest factual knowledge in our possession. The information was up-to date on the date this document was printed (latest versions can always be supplied upon request). Although the data is considered accurate, we cannot guarantee accuracy, the results obtained from its use, or any patent infringement resulting from its use (unless this is contractually and explicitly agreed in writing, in advance). The data is supplied on the condition that the user shall conduct tests to determine materials suitability for particular application. The Heraeus logo and Heraeus, figurative mark are trademarks or registered trademarks of Heraeus Holding GmbH or its affiliates. All rights reserved.