

## PCC11915

### Conductor

#### Description

PCC11915 is a silver conductor designed for cost-sensitive hybrid applications.

#### Key Features

- Excellent rheological properties
- Excellent adhesion
- Solder leach resistant



*This picture does not show the packaging of PCC11915 and is solely intended for illustration purposes. The products are available in different packaging configurations and may change over time. Please refer to the latest safety data sheets for safety-relevant pictograms.*

#### Typical Properties

Viscosity	120-140 Kcps Brookfield HBT Spindle CP-51, 1 rpm, 25 °C
Alloy Ratio	100
Metal	Ag

#### Recommended Processing Guide

Process Temperature (TDS)	850-925 °C peak temperature. Dwell time of 5-10 minutes.
Film Thickness	9-15 um

#### Americas

Phone +1 610 825 6050  
electronics.americas@heraeus.com

#### Asia Pacific

Phone +65 6571 7649  
electronics.apac@heraeus.com

#### China

Phone +86 53 5815 9601  
electronics.china@heraeus.com

#### Europe, Middle East and Africa

Phone +49 6181 35 4370  
electronics.emea@heraeus.com

The descriptions and engineering data shown here have been compiled by Heraeus using commonly accepted procedures, in conjunction with modern testing equipment, and have been compiled according to the latest factual knowledge in our possession. The information was up-to date on the date this document was printed (latest versions can always be supplied upon request). Although the data is considered accurate, we cannot guarantee accuracy, the results obtained from its use, or any patent infringement resulting from its use (unless this is contractually and explicitly agreed in writing, in advance). The data is supplied on the condition that the user shall conduct tests to determine materials suitability for particular application. The Heraeus logo and Heraeus, figurative mark are trademarks or registered trademarks of Heraeus Holding GmbH or its affiliates. All rights reserved.