

PD5200Black

Polymer Thick Film

Description	Typical Properties	
	Viscosity	70 – 140 kcps
Recommended Processing Guide		
	Printing Parameters	Steel Mesh (280 TPI)
	Drying Temperature	150°C
	Film Thickness	40 -50 µ per layer
	Recommended Thinner	Heraeus RV-221
	Paste Compatibility	Compatible with all PriElex products

PD5200Black

Polymer Thick Film

Warranty

Material guaranteed to meet specifications for 3 months from date of manufacturing with proper storage.

Storage

Ambient storage, mix well prior to use.

Americas

Phone +1 610 825 6050

electronics.americas@heraeus.com

Asia Pacific

Phone +65 6571 7649

electronics.apac@heraeus.com

China

Phone +86 53 5815 9601

electronics.china@heraeus.com

Europe, Middle East and Africa

Phone +49 6181 35 4370

electronics.emea@heraeus.com

The descriptions and engineering data shown here have been compiled by Heraeus using commonly accepted procedures, in conjunction with modern testing equipment, and have been compiled as according to the latest factual knowledge in our possession. The information was up-to date on the date this document was printed (latest versions can always be supplied upon request). Although the data is considered accurate, we cannot guarantee accuracy, the results obtained from its use, or any patent infringement resulting from its use (unless this is contractually and explicitly agreed in writing, in advance). The data is supplied on the condition that the user shall conduct tests to determine materials suitability for particular application. The Heraeus logo and Heraeus, figurative mark are trademarks or registered trademarks of Heraeus Holding GmbH or its affiliates. All rights reserved.