

PdCu15**Hera 614****General information**

Applications	sliding contacts, contacts
Product Forms	wire, strip
Density, g/cm ³	11.39
Melting Range, °C	1370 - 1400

Forming Processes

Forming Process	can be roll clad
-----------------	------------------

Chemical Properties

Corrosion Resistant	
---------------------	--

Physical properties

Conductivity, min., % IACS	4.27
Conductivity, max., % IACS	4.32
Coefficient of Expansion (20 - 200 °C) (x 10 ⁻⁶), K ⁻¹	12.31
Young's Modulus, GPa	172
Modulus of Rigidity, GPa	50

Temper	Property Range
Hardness, HV	110 - 240
Tensile Strength, MPa	400 - 780
Yield Strength, MPa	200 - 750
Elongation, %	> 20

Contact

precious.metals@heraeus.com | www.heraeus-precious-metals.com

[Looking for more data?](#)

The information in this data sheet contains only general information on the use of our products or examples for their application. They do not release the customer from a careful inspection of the delivered product for its fitness for the customer's particular purpose of use. Any customer's special requests regarding the particular use of a product will only be authoritative if Heraeus has confirmed to the customer in writing at the time of conclusion of a corresponding contract that the product delivered is fit for the customer's intended use. Heraeus, therefore, does not guarantee the correctness and completeness of the information regarding the customer's intended use. The customer's purchase will be governed exclusively by the written order confirmation of Heraeus and the Heraeus General Terms of Sale and Delivery, which are available at www.heraeus.com/gtc. This data sheet may be subject to changes at any time.