

PdAg38Cu15 | similar to ASTM B563

Hera 649

General information

Applications	slip rings, contacts, potentiometer wire, sliding contacts
Product Forms	wire, strip, sheet
Density, g/cm ³	10.85
Melting Range, °C	1070 - 1130

Forming Processes

Age Hardenable	Yes
Material Behaviour	ductile
Forming Process	machinable, formable, can be roll clad

Chemical Properties

Comment	Oxidation resistant up to 300 °C
---------	----------------------------------

Physical properties

Conductivity, min., % IACS	6.2
Conductivity, max., % IACS	7
Young's Modulus, GPa	106

	Annealed	Stress Relieved	Age Hardened	Property Range
Hardness, HV	180 - 220	250 - 340	320 - 390	180 - 390
Tensile Strength, MPa	580 - 680	850 - 1050	1000 - 1350	580 - 1350
Elongation, %	> 15	2 - 9	< 3	< 3

Contact

precious.metals@heraeus.com | www.heraeus-precious-metals.com
Heraeus Precious Metals GmbH & Co. KG | Heraeusstrasse 12-14 | 63450 | Hanau | Germany

[Looking for more data?](#)

The information in this data sheet contains only general information on the use of our products or examples for their application. They do not release the customer from a careful inspection of the delivered product for its fitness for the customer's particular purpose of use. Any customer's special requests regarding the particular use of a product will only be authoritative if Heraeus has confirmed to the customer in writing at the time of conclusion of a corresponding contract that the product delivered is fit for the customer's intended use. Heraeus, therefore, does not guarantee the correctness and completeness of the information regarding the customer's intended use. The customer's purchase will be governed exclusively by the written order confirmation of Heraeus and the Heraeus General Terms of Sale and Delivery, which are available at www.heraeus.com/gtc. This data sheet may be subject to changes at any time.