

### Platinum

Pt

#### General information

Applications	crucibles, casting dishes, electrodes, semi-finished products, laboratory equipment (crucibles), crystal growth crucibles, glass manufacturing, thermocouple thimbles
Product Forms	wire, sheet, tube
Density, g/cm <sup>3</sup>	21.45
Melting Point, °C	1769

#### Forming Processes

Age Hardenable	No
Material Behaviour	ductile
Forming Process	formable, machinable, can be roll clad

#### Physical properties

Conductivity, min., % IACS	15.78
Conductivity, max., % IACS	16.07
Thermal Conductivity at 20 °C, W/(m*K)	74
Young's Modulus, GPa	170
Modulus of Rigidity, GPa	66

	Annealed	Work Hardened	Property Range
Hardness, HV	42	98	42 - 98
Tensile Strength, MPa	150	330	150 - 330
Yield Strength, MPa	70	290	70 - 290
Elongation, %	40	3	3 - 40

#### Contact

precious.metals@heraeus.com | www.heraeus-precious-metals.com  
 Heraeus Precious Metals GmbH & Co. KG | Heraeusstrasse 12-14 | 63450 | Hanau | Germany



Looking for more data?

The information in this data sheet contains only general information on the use of our products or examples for their application. They do not release the customer from a careful inspection of the delivered product for its fitness for the customer's particular purpose of use. Any customer's special requests regarding the particular use of a product will only be authoritative if Heraeus has confirmed to the customer in writing at the time of conclusion of a corresponding contract that the product delivered is fit for the customer's intended use. Heraeus, therefore, does not guarantee the correctness and completeness of the information regarding the customer's intended use. The customer's purchase will be governed exclusively by the written order confirmation of Heraeus and the Heraeus General Terms of Sale and Delivery, which are available at [www.heraeus.com/gtc](http://www.heraeus.com/gtc). This data sheet may be subject to changes at any time.