

### AgCu20

#### General information

Applications	slip rings, sliding contacts, switching contacts, contacts
Product Forms	strip, wire
Density, g/cm <sup>3</sup>	10.13
Melting Range, °C	779 - 820

#### Forming Processes

Material Behaviour	ductile
--------------------	---------

#### Chemical Properties

Comment	Susceptible to attack by sulphur
---------	----------------------------------

#### Physical properties

Conductivity, min., % IACS	70
Conductivity, max., % IACS	77
Coefficient of Expansion (20 - 100 °C) (x 10 <sup>-6</sup> ), K <sup>-1</sup>	19.3
Young's Modulus, GPa	85

	Annealed	Work Hardened	Property Range
Hardness, HV	80 - 120	130 - 190	80 - 190
Tensile Strength, MPa	300 - 400	450 - 700	300 - 700
Yield Strength, MPa	200 - 300	450 - 600	200 - 600
Elongation, %	> 20	2 - 4	2 - 20

#### Contact

precious.metals@heraeus.com | www.heraeus-precious-metals.com  
 Heraeus Precious Metals GmbH & Co. KG | Heraeusstrasse 12-14 | 63450 | Hanau | Germany



Looking for more data?

The information in this data sheet contains only general information on the use of our products or examples for their application. They do not release the customer from a careful inspection of the delivered product for its fitness for the customer's particular purpose of use. Any customer's special requests regarding the particular use of a product will only be authoritative if Heraeus has confirmed to the customer in writing at the time of conclusion of a corresponding contract that the product delivered is fit for the customer's intended use. Heraeus, therefore, does not guarantee the correctness and completeness of the information regarding the customer's intended use. The customer's purchase will be governed exclusively by the written order confirmation of Heraeus and the Heraeus General Terms of Sale and Delivery, which are available at [www.heraeus.com/gtc](http://www.heraeus.com/gtc). This data sheet may be subject to changes at any time.