

AgCu10

Hera 342

General information

Applications	sliding contacts, contacts
Product Forms	sheet, wire
Density, g/cm ³	10.3
Melting Range, °C	779 - 875

Forming Processes

Material Behaviour	ductile
Forming Process	formable, machinable, can be roll clad

Chemical Properties

Comment	sensitive to sulphur, not oxidation resistant
---------	---

Physical properties

Conductivity, min., % IACS	81.9
Conductivity, max., % IACS	86
Thermal Conductivity at 20 °C, W/(m*K)	344
Coefficient of Expansion (20 - 100 °C) (x 10 ⁻⁶), K ⁻¹	19.4
Young's Modulus, GPa	81
Modulus of Rigidity, GPa	28

	Property Range
Hardness, HV	65 - 120
Tensile Strength, MPa	250 - 550
Yield Strength, MPa	200 - 500
Elongation, %	2 - 20

Contact

precious.metals@heraeus.com | www.heraeus-precious-metals.com
 Heraeus Precious Metals GmbH & Co. KG | Heraeusstrasse 12-14 | 63450 | Hanau | Germany



Looking for more data?

The information in this data sheet contains only general information on the use of our products or examples for their application. They do not release the customer from a careful inspection of the delivered product for its fitness for the customer's particular purpose of use. Any customer's special requests regarding the particular use of a product will only be authoritative if Heraeus has confirmed to the customer in writing at the time of conclusion of a corresponding contract that the product delivered is fit for the customer's intended use. Heraeus, therefore, does not guarantee the correctness and completeness of the information regarding the customer's intended use. The customer's purchase will be governed exclusively by the written order confirmation of Heraeus and the Heraeus General Terms of Sale and Delivery, which are available at www.heraeus.com/gtc. This data sheet may be subject to changes at any time.