

AgPd30Cu5

Hera 625

General information

Applications	sliding contacts, contacts
Product Forms	wire, sheet
Density, g/cm ³	10.8
Melting Range, °C	1120 - 1165

Forming Processes

Age Hardenable	No
Material Behaviour	ductile
Forming Process	can be roll clad

Chemical Properties

Comment	corrosion resistant
---------	---------------------

Physical properties

Conductivity, min., % IACS	10.96
Conductivity, max., % IACS	11.32
Coefficient of Expansion (20 - 200 °C) (x 10 ⁻⁶), K ⁻¹	15.8
Young's Modulus, GPa	106
Modulus of Rigidity, GPa	39

	Annealed	Work Hardened	Property Range
Hardness, HV	70 - 120	190 - 250	70 - 250
Tensile Strength, MPa	300 - 500	650 - 800	300 - 800
Elongation, %	> 20	< 5	2 - 25

Contact

precious.metals@heraeus.com | www.heraeus-precious-metals.com
 Heraeus Precious Metals GmbH & Co. KG | Heraeusstrasse 12-14 | 63450 | Hanau | Germany



Looking for more data?

The information in this data sheet contains only general information on the use of our products or examples for their application. They do not release the customer from a careful inspection of the delivered product for its fitness for the customer's particular purpose of use. Any customer's special requests regarding the particular use of a product will only be authoritative if Heraeus has confirmed to the customer in writing at the time of conclusion of a corresponding contract that the product delivered is fit for the customer's intended use. Heraeus, therefore, does not guarantee the correctness and completeness of the information regarding the customer's intended use. The customer's purchase will be governed exclusively by the written order confirmation of Heraeus and the Heraeus General Terms of Sale and Delivery, which are available at www.heraeus.com/gtc. This data sheet may be subject to changes at any time.