

### PtAu5

#### General information

Applications	electrodes, crucibles, casting dishes, laboratory equipment (crucibles), semi-finished products, thermocouple thimbles
Product Forms	wire, sheet, tube
Density, g/cm <sup>3</sup>	21.3
Melting Range, °C	1675 - 1745

#### Forming Processes

Age Hardenable	No
Material Behaviour	ductile
Forming Process	formable, machinable

#### Physical properties

Conductivity, min., % IACS	9.1
Conductivity, max., % IACS	9.4
Young's Modulus, GPa	183
Modulus of Rigidity, GPa	62

	Annealed	Work Hardened
Hardness, HV	139	194
Tensile Strength, MPa	460	635
Yield Strength, MPa	370	610
Elongation, %	7	1

#### Contact

precious.metals@heraeus.com | www.heraeus-precious-metals.com  
 Heraeus Precious Metals GmbH & Co. KG | Heraeusstrasse 12-14 | 63450 | Hanau | Germany



Looking for more data?

The information in this data sheet contains only general information on the use of our products or examples for their application. They do not release the customer from a careful inspection of the delivered product for its fitness for the customer's particular purpose of use. Any customer's special requests regarding the particular use of a product will only be authoritative if Heraeus has confirmed to the customer in writing at the time of conclusion of a corresponding contract that the product delivered is fit for the customer's intended use. Heraeus, therefore, does not guarantee the correctness and completeness of the information regarding the customer's intended use. The customer's purchase will be governed exclusively by the written order confirmation of Heraeus and the Heraeus General Terms of Sale and Delivery, which are available at [www.heraeus.com/gtc](http://www.heraeus.com/gtc). This data sheet may be subject to changes at any time.