

Platinum DPH

Pt DPH

Platinum DPH is an oxide dispersion hardened grade of pure platinum.

It is commonly used in high temperature applications when the use of Rhodium cannot be tolerated or in times of high Rhodium prices (e. g. crucibles and equipment for processing special optical glasses). It is also used as a lining for refractory components or in thermocouple sheaths for the use in glass melts.

The hardening which results from the oxide particles, represents the most effective strengthening mechanism of the material. Due to the modified microstructure, DPH is considerably less sensitive to corrosion processes along the grain boundaries than comparable materials. These characteristics allow for extended life and results in the precious metal to be used more economically. An example would be reduced wall thicknesses of Pt DPH compared to Pt.

General information

Applications	crucibles, electrodes, casting dishes, semi-finished products, glass manufacturing, crystal growth crucibles, thermocouple thimbles
Product Forms	wire, sheet, tube
Density, g/cm ³	21.45
Melting Point, °C	1769

Forming Processes

Material Behaviour	ductile
Forming Process	machinable, formable

Mechanical Properties

Hardness, HV	60
Tensile Strength, MPa	178
Yield Strength, MPa	73
Elongation, %	22

Contact

precious.metals@heraeus.com | www.heraeus-precious-metals.com
 Heraeus Precious Metals GmbH & Co. KG | Heraeusstrasse 12-14 | 63450 | Hanau | Germany




Looking for more data?

The information in this data sheet contains only general information on the use of our products or examples for their application. They do not release the customer from a careful inspection of the delivered product for its fitness for the customer's particular purpose of use. Any customer's special requests regarding the particular use of a product will only be authoritative if Heraeus has confirmed to the customer in writing at the time of conclusion of a corresponding contract that the product delivered is fit for the customer's intended use. Heraeus, therefore, does not guarantee the correctness and completeness of the information regarding the customer's intended use. The customer's purchase will be governed exclusively by the written order confirmation of Heraeus and the Heraeus General Terms of Sale and Delivery, which are available at www.heraeus.com/gtc. This data sheet may be subject to changes at any time.

Platinum DPH


Pt DPH

Creep Rupture




source: measured and extrapolated

Norton




source: measured and extrapolated

Creep Rupture – Comparison



source: measured and extrapolated

High Temperature Tensile Test



source: measured

Contact

precious.metals@heraeus.com | www.heraeus-precious-metals.com
 Heraeus Precious Metals GmbH & Co. KG | Heraeusstrasse 12-14 | 63450 | Hanau | Germany



Looking for more data?

The information in this data sheet contains only general information on the use of our products or examples for their application. They do not release the customer from a careful inspection of the delivered product for its fitness for the customer's particular purpose of use. Any customer's special requests regarding the particular use of a product will only be authoritative if Heraeus has confirmed to the customer in writing at the time of conclusion of a corresponding contract that the product delivered is fit for the customer's intended use. Heraeus, therefore, does not guarantee the correctness and completeness of the information regarding the customer's intended use. The customer's purchase will be governed exclusively by the written order confirmation of Heraeus and the Heraeus General Terms of Sale and Delivery, which are available at www.heraeus.com/gtc. This data sheet may be subject to changes at any time.